

Article Identifier: <https://identifier.visnav.in/1.0001/ijacbs-22c-23010/>

An Overview on Green synthesis of Nanoparticles and their Advanced Applications in Sustainable Agriculture

Aamir A. Aslam ^{1*}, Muhammad S. Aslam ², Awais A. Aslam ³

¹ Institute of Physics, Riphah International University, Lahore, Pakistan

² Department of Mathematics, University of Lahore, Lahore, Pakistan

³ Department of Chemistry, COMSATS University Islamabad, Lahore, Pakistan

* For correspondence: havard786@gmail.com

Received on: 23 March 2022

Published on: 26 April 2022

ABSTRACT

The excess use of unsafe pesticides and mineral fertilizers in agriculture has led to serious health problems and environmental pollution. Nanotechnology has been solving these problems by providing nanoparticles (NPs) with excellent performance. By green synthesis of nanoparticles from plants, animals, and microbes, the use of hazardous and toxic chemicals has become limited. Nanoparticles have excellent performance in many fields such as electronics, cosmetics, automobiles, catalysis, biosensors, bioengineering, etc. NPs also showed excellent performance in agriculture by improving crop production and food quality. Various nano-based agro particles have many smart and efficient agricultural systems involving Nano pesticides, Nano fertilizers, Nano herbicides etc. Apart from enhancing the food production, these materials operate some other functions like as identifying disease in plants, control release of nutrients, delivery of nutrients at target sites, etc. various nano-fertilizers such as Fe, Mn, N, K, Mo, P, CNTs and P showed excellent targeted delivery performance. Nano-pesticides and many nano-formulations have showed excellent pest protection performance. Here we reviewed the sources of nano-materials and their excellent performance in agriculture.

Keywords: nanoparticles, Nano pesticides, Nano fertilizers, Nano herbicides, sustainable agriculture, nanotechnology

1. INTRODUCTION

Nanoparticles have dimension in the range of 1-100 nanometer (nm) and enact as a tie between materials of different magnitude and molecular or atomic entities [1]. They manifest exceptional and miraculous attributes because of their higher reactivity's which in turn is due to their large surface areas and smaller sizes [2-4]. Beginning of the nineteenth century has brought the

attention of scientists towards the capacity of biological entities to curtail the metal antecedents but the processes are still undetermined. Population explosion, urbanization and speedy industrialization have ended up in the ruin of earth's atmosphere and tremendous amount of unhealthy matter is in air. More knowledge is to be discerned about the secrets of nature and its natural products which would lead to the advancements in the field of nanoparticles' synthesis. Nanoparticles are

widely implied in different era of research and most significantly in the field of agriculture. Nanomaterial's have many applications in different fields such as paints, semi-conducting devices, cosmetics, medicines, etc. (figure 1). Therefore the syntheses processes need to be developed that do not utilize toxic reagents. Hence, green synthesis of nanoparticles turns out to be a suitable alternative to physical and chemical methods [5-7]. Nanoparticles manufactured through biological methods have gained much favor over nanoparticles synthesized from physical or chemical methods. NPs synthesized from physico-chemical methods come out with many problems such as the utilization of toxic reagents and hazardous by-products [8]. Plant based (green) synthesis of nanoparticles is evidently not a hazardous method as metal salt is synthesized by the use of plant extract. Green synthesis is the procedure for the development of nanoparticles which makes use of natural resources such as plant extracts, micro-organisms and energy conserving processes in a more economical, non-toxic and sustainable way [9-10]. Green nano-technology is an energy efficient and safer process. It minimizes wastes production and green-house gas emissions. Renewable material utilization for such products is very beneficial

and has lesser environmental impacts in terms of energy and pollution and so is termed as eco-friendly. In order to be utilized for specific applications, extracts from different plants are used in the production of NPs with characteristic functionalities. Micro-organisms like bacteria, yeasts, algae and fungi are used. Choice of micro-organisms depends on functionalities, size and type of the desired nanoparticles [11]. Green synthesis which utilizes biological molecules from plant extracts has turned out to be of much significance as compared to chemical means as plants are safe, promptly available and diverse which makes it fit for a sustainable bio-resource. The reaction rates for plant mediated synthesis of nanoparticles are higher ranging from few minutes to hours and reaction primarily can take place at room temperature. The exercise of plant extracts to manufacture high quality nanoparticles is in huge practice because of simple steps involved in recovering nanoparticle. The steps are abstraction of plant, extract filtration and metal NP salt addition. Resultant solution is stirred and NPs are eventually recovered from precipitate [9].

Involvement of nanotechnology in agriculture sector has inclined to be a vital factor for sustainable development.




Figure 1. Applications of nanomaterials in different fields

It has a great potential to transform the whole agricultural sector with innovative means which enhance the agricultural productivity of plants through adept supplements in the mode of nano-nutrients for nano-fertilizers, nano-pesticide and nano-herbicides by the plants [12]. Nano-materials are utilized for plants' protections as nano-herbicides, nano-pesticides and nano-sensors as well. Nano-nutrients or nano-fertilizers have tremendous effects on growth, rate of germination, phytotoxic of various field crops and vegetables [13].

Nanoparticles being comparable to virus in size may be inhaled by humans and may end up in bloodstream or other sites in the human body like heart, blood cells or liver [14-15]. As toxicity of the NPs depends on origin, many of the NPs may have non-toxic or positive effects on health. Exposure to NPs might have general acute toxic effects which include protein denaturation, generation of reactive oxygen species, perturbations in phagocytic functions and also in mitochondrial disconcertion. Other common and chronic toxic effects of NPs may include neo-antigens' generation which results in enlargement or dysfunctioning of the organs [15].

2. SYNTHESIS OF NANOPARTICLES

The biological preparation of Nanoparticles via the green method utilizes the plants and animals to cause the conversion of metallic ions into neutral atoms. Green synthesis (GS) is also done by the elimination of toxic chemicals. Hence, the green synthesized nanoparticles (NPs) offer you the improved biocompatibility in dealing with the biomedical application as compared to the chemically synthesized ones.

There are multiple plant species and groups, among which the Angiosperms and Algae are widely studied. The green-synthesis from the plants-derived materials such as chitin and silk also reported in the past. Different kinds of researches in the past have proved the capability of various plants' specie in green synthesis of

nanoparticles and their capping behavior. Not just the plants but the animal-derived biomolecules are also responsible for this.

2.1. Plant-based synthesis of Nanoparticles

This section will highlight all the signs of progress made towards the green synthesis of nanoparticles via the plant species. Most commonly, the plant species having medicinal applications play a major role in the green synthesis process (table 1).

2.1.1. Angiosperms

The plant's lineage has the angiosperms at the top and hence these are widely utilized for the green synthesis of NPs. Their easy access, wide applications, availability all over the world has further favored this synthesis. Also, the Angiosperms play an essential role in dealing with human and animal diseases [16]. The nature of Angiosperm plants have aided in processing the natural reducing ability in improving this green domain. The green Synthesis has received many updates in its library especially in the Asian Countries due to enriched plant resources. But not all the plant's species can do justice with the green synthesis of plants.

Most of the researches made on the angiosperm species have revealed that the synthesis of Gold and Silver Nanoparticles is quite common as compared to the other magnetic Nanoparticles. The reason behind this fact is the poor capability of converting the metal cation into lower reduction potential. Various researches have contributed to the plant-based production of nanoparticles. A well-explored plant named *Camellia sinensis* has been considered an advantageous plant's specie in GS of NPs. The purification of living molecules present in this plant's species viz. catechins, theaflavins, and their isolation has confirmed their role in green synthesis of Au NPs [17-18]. Similarly, the pure tea polyphenol is utilized for the synthesis of Pt NPs. Another plant's specie named *Jatropha curcas* L is

Table 1. List of nanoparticles derived from plants

Plant	Nanoparticle	Size (nm)	Ref.
<i>Allium cepa</i> L.	Au	~100	[35]
<i>Allium sativum</i> L.	Ag	4.4 ± 1.5	[36]
<i>Achyranthus aspera</i> L.	Ag	20-30	[37]
<i>Anacardium occidentale</i> L.	Au	-	[38]
<i>Andrographis paniculata</i> Nees.	Ag	28	[39]
<i>Astragalus gummifer</i> Labill.	Ag	13.1±1.0	[40]
<i>Azadirachta indica</i> A. Juss.	Au	2-100	[41]
<i>Camellia sinensis</i> L.	Au	25	[42]
<i>Carica papaya</i> L.	Ag	15	[43]
<i>Centella asiatica</i> L.	Ag	-	[44]
<i>Chenopodium album</i> L.	Ag Au	12,10	[45]
<i>Coleus aromaticus</i> Lour.	Ag	40-50	[46]
<i>Cinnamomum zeylanicum</i> Blume.	Pd	15 to 20	[47]
<i>Cinnamomum camphora</i> L.	Pd	3.2-6.0	[48]
<i>Citrullus colocynthis</i> L.	Ag	31	[49]
<i>Datura metel</i> L.	Ag	16 - 40	[50]
<i>Desmodium triflorum</i> (L) DC.	Ag	5-20	[51]
<i>Diopyros kaki</i>	Pt	2-12	[52]
<i>Dioscorea bulbifera</i> L.	Ag	8-20	[53]
<i>Dioscorea oppositifolia</i> L.	Ag	14	[54]
<i>Elettaria cardamomom</i> (L) Maton.	Ag	-	[55]
<i>Gardenia jasminoides</i> Ellis.	Pd	3-5	[56]
<i>Glycyrrhiza Glabra</i> L.	Ag	20	[57]
<i>Hibiscus cannabinus</i> L.	Ag	9	[58]
<i>Hydrilla verticilata</i> (L.f.) Royle.	Ag	65.55	[59]
<i>Jatropha curcas</i> L.	ZnS	10	[60]
<i>Justicia gendarussa</i> L.	Au	27	[61]
<i>Lantana camara</i> L.	Ag	12.55	[62]
<i>Leonuri herba</i> L.	Ag	9.9 - 13.0	[63]
<i>Macrotyloma uniflorum</i> (Lam) Verdc.	Au	14-17	[64]
<i>Mentha piperita</i> L.	Ag, Au	90, 150	[65]
<i>Mirabilis jalapa</i> L.	Au	100	[66]
<i>Morinda pubescens</i> L.	Ag	25-50	[67]
<i>Ocimum sanctum</i> L.	Ag	4-30	[68]
<i>Parthenium hysterophorus</i> L.	Ag	10	[69]
<i>Pedilanthus tithymaloides</i> (L) Poit.	Ag	15-30	[70]
<i>Piper betle</i> L.	Ag	3-37	[71]
<i>Piper nigrum</i> L.	Ag	5 - 50	[72]
<i>Plumeria rubra</i> L.	Ag	32 -220	[73]
<i>Sesuvium portulacastrum</i> L.	Ag	5-20	[74]
<i>Solanum xanthocarpum</i> L.	Ag	10	[75]
<i>Sorghum</i> Moench.	Ag, Fe	10, 50	[76]
<i>Soybean (Glycine Max)</i> L.	Pd	~15	[77]
<i>Swietenia mahogany</i> (L) Jacq.	Ag	-	[78]
<i>Syzygium aromaticum</i> (L) Merr. & Perr.	Au	5-100	[79]
<i>Terminalia catappa</i> L.	Au	10-35	[80]
<i>Trianthema decandra</i> L.	Ag	10-50	[81]
<i>Tridax procumbens</i> L.	CuO ₂	-	[82]
<i>Vitis vinifera</i> L.	Pb	661	[83]
<i>Zingiber officinale</i> Rosc.	Ag Au	10	[84]

responsible for the reduction of metal cations via the cyclic peptide molecules [19]. Therefore, the overall research progress that has been completed recently in this newly-emerged green synthesis domain is quite impressive as compared to the conventional methods.

2.1.2. Gymnosperms

Gymnosperms were the first to have the seeds in plants category, hence they are of much importance. Each group of plants further has distinct metabolites. These metabolites are further responsible for the reduction of metal ions to synthesize the nanoparticles. The studies regarding the green synthesis of NPs from gymnosperms is quite restricted but evident to some extent. Various researches have been made in this sense, and the NPs synthesized from the gymnosperms have different sizes, morphology, and quantity depending on plant type [20-24]. Noruzi *et al.*, (2012) have synthesized the Au NPs from the *Thuja orientalis* extract in just 10-minutes of reaction time. The overall efficiency was found out to be 90% and the produced Nanoparticles were round in shape and crystalline in nature [25].

2.1.3. Algae

The three main criteria to synthesize and hence achieve the efficiency in the GS of NPs are mainly the reducing agent, stabilizing capping agent, and acceptable solvent [26]. The algae-based preparation of nanoparticle is one such process. These are photoautotrophic in nature [27]. Hence, the bio-reduction of algae can synthesize the metal and metal oxide NPs [28-32]. *Spirulina platensis* is a kind of edible blue-green alga that is utilized to synthesize the gold and silver NPs [33]. Senapati *et al.*, (2012) have synthesized the gold NPs via *Tetraselmis kochinensis* plant [34].

2.2. Green synthesis of Nanoparticles from Animal-derived material

Polymer nanomaterial's have their unique and distinct properties depending on their surface area, microbial encumbrance, and the size of pores. Many animals' species either unicellular or multicellular are involved in the synthesis of NPs.

2.2.1. Silk Proteins

Multiple species of insects and spiders made the silk fibroin which is a semi-crystalline polymer containing amino acids like glycine, alanine, and serine. This material is employed in the tissue engineering of bones, skin, muscles, and blood vessels. The basic reason is its non-toxic, less harmful, and non-immunogenic nature. Multiple evidences have been found regarding the green synthesis of nano-composites via the utilization of fibroin. The most common is the fibroin-TiO₂ [85] nano-composites and the nano-hydroxyapatite silk fibroin [86]. All the obtained Nano composites were crystalline in nature and 100 nm in length. Another component named sericin, which is present in the effluents of silk industries is also responsible for the synthesis of NPs. The nano-sericin powder is obtained via the ultra-sonification which reduces the particle size [87].

2.2.2. Chitosan

The invertebrate chitin is responsible for providing you the multiple applications in various fields. For example, the chitosan nano-fibers are perfect to colorize the textiles. Moreover, the medical field is also benefited from this peptide. It is involved in the slow release of vaccines as well as cancer treatment. Nano-chitosan also plays a noteworthy role in reducing the contamination of environment. Furthermore, Sahab *et al.*, (2015) have synthesized the PAA NPs of the 50 nm size which have the anti-fungal uses [88].

The magnetic chitosan plays a major role in removing the organic dyes from the wastewater. The large quantity of hydroxyl as well as amino groups present in chitosan are responsible for a good adsorption rate against the

organic dyes when used with the magnetism of Fe₃O₄ [89]. Similarly, synthetic dyes can also be removed via the bentonite-chitosan nano-composites [90].

2.3. Microbes-based synthesis of Nanoparticles

There had been a number of techniques and processes employed to obtain the nanoparticles by different precursors [91-92]. Some of the techniques were not budget-friendly while some were toxic due to the excessive use of chemicals, while the rest synthesize the NPs via the UV radiation or aerosol spray [92-93]. Hence, to minimize all these problems, the microbes-based synthesis of NPs are practiced significantly [93]. The microbes-based synthesis of NPs has now become an interesting research to make and has a bright future ahead as well due to the number of applications [91, 93-94].

The nanomaterials are obtained from the microbes via two different methods including the intracellular and extracellular [91, 95]. Their mechanism is different as per the species and NPs you want to obtain. The intracellular mechanism is based on the transfer of

positive metal ions through the cell wall which is due to the negative ions already present in the cell wall of bacteria. These ions were then reduced by the specific proteins i.e. enzymes into the NPs. While, in fungi the extracellular mechanism takes place. In this approach, the metal ions are converted to their respective NPs via the nitrate-reductase synthesis method [95]. *F. oxysporum* produces the silver-gold NPs via this extracellular approach when reacts with the Tetrachloroaurate and Silver Nitrate [96]. Also, *Aspergillus flavus* is involved in the green synthesis of Ag NPs having a size of 8 nm approximately [97] (table 2).

3. SUSTAINABLE AGRICULTURE

The idea of sustainable development of agriculture gained immense importance after Brundtland Report in 1987. Though its meaning is little vague, United States Department of Agriculture 2012 defined it "agriculture is basically about livestock and production of various crops having impact on environment". The basic concept behind sustainable development of agriculture is to maintain balance between need of food and protecting the environmental resources from declining resources

Table 2. Biosynthesis of nanoparticles from microbes

Sr. No	Microorganism	Nanoparticle	Size (nm)	Ref.
1	<i>Lactobacillus sp.</i>	Ti	40-60	[98]
2	<i>P. boryanum UTEX 485</i>	Pt	30-0.3	[99]
3	<i>Corynebacterium sp. SH09</i>	Ag	10-15	[100]
4	<i>Desulfovibrio desulfuricans</i>	Pd	50	[101]
5	<i>Lactobacillus sp.</i>	Au	20-50	[102]
6	<i>Pseudomonas stutzeri AG259</i>	Ag	<200	[103]
7	<i>Klebsiella pneumoniae</i>	CdS	5-200	[104]
8	<i>Aquaspirillum magnetotacticum</i>	Fe ₃ O ₄	40-50	[105]
9	<i>Bacillus subtilis 168</i>	Au	5-25	[106]
10	<i>Coriolus versicolor</i>	Ag	25-75	[107]
11	<i>Aspergillus flavus</i>	Ag	8.9	[108]
12	<i>V. luteoalbum and isolate 6-3</i>	Au	<10	[109]
13	<i>F. oxysporum</i>	BaTiO ₃	4	[110]
14	<i>F. oxysporum</i>	Pt	10-50	[111]
15	<i>F. oxysporum</i>	Si	6-13	[112]
16	<i>F. oxysporum</i>	Ti	5-15	[112]
17	<i>F. oxysporum</i>	Au, Ag	8, 14	[113]

and harmful effects. There are many other aims associated with this sustainable approach like less usage of inorganic fertilizers, protection of water resources, conservation of biodiversity, minimizing waste production etc. [114-115]. Ecofriendly fertilizers have been recognized to increase the crop yield along with better condition of soil [116-119]. To help farmers financially, helping them to implement new techniques and providing them better facilities to upgrade their quality of life is also included in their objectives of sustainable approach [120] (figure 2).

Various farming techniques can be applied to make it better to a certain level. Nanotechnology is one of the progressive and successful techniques to produce a highly efficient fertilizer which brings no harm to biodiversity. Agriculture is one of the areas which is totally shifted from conventional techniques to nanotechnology. Use of nano-fertilizers has taken the place of inorganic pesticides because they tend to enhance crop yield and also stimulated sustainable approach widely.

4. NANOAGRICULTURE A WAY TOWARDS

SUSTAINABLE AGRICULTURE

Modern agriculture demands sustainable and high crop yield without use of inorganic chemical fertilizers which has adverse effects on health and environment. Hazardous chemicals found in such fertilizers reach under the soil bed via leaching and contaminate water which leads to detrimental outputs. However, preventing measures should be taken to reduce the unwanted and harmful risks produced by chemical fertilizers [121]. Agricultural approach based on nanotechnology is a successful method to obtain attractive yield[122] and production of nano-devices like nano-biosensors (that senses the disease in crops) is a major innovation in the field of agriculture [123]. Other features have been introduced into the nano-biosensors to detect any toxicity caused by microorganisms in plants. Moreover, the very small size of this device makes it very easy to use in agricultural lands and fields and these bio-nanosensors are also used to detect toxicity caused by fungi [123-125]. Hence, use of nanoparticles in the conventional agriculture system has gained immense importance due to its countless benefits which includes




Figure 2. The different parts of sustainable agriculture




Figure 3. Role of nanoparticles in agriculture

improved quality of soil, smart monitoring, enhanced enzymatic activity, increased nutrients uptake etc. and now this approach is known as nanoagriculture. Figure 3 illustrates the role of nanoparticles in agriculture.

NPs reduce the nutrient loss thus enhancing the crop production via precise control of nutrients [126-127]. The present condition of agricultural system is not suitable for better yield but incorporation of nanotechnology with present system would be able to make it better with use of efficient nano devices and nano-fertilizers considerably [128]. Sustainable methods of agriculture are getting attention recently for its many advantages and environmental friendly nature.

5. APPLICATIONS OF NANOPARTICLES IN AGRICULTURE

5.1. Weed Control by Nano-herbicide

Herbicide resistance is quite common in the cropped environment due to number of reasons. One most common reason that results in the poor weed control

and herbicide resistance is the multi-specie approach. Plants can get exposed to one herbicide in one season while a different one in another season. It develops the resistance against the herbicides. Weeds can be controlled by producing an herbicide that attacks the roots of target weeds. Developing this specific herbicide molecule requires the nanoparticle (NP) encapsulation which then enters the roots of weeds to inhibit the glycolysis process. It'll create the starvation condition and particular weed get killed [129]. Applying herbicide in the soil which doesn't have sufficient moisture will lead to unfavorable results. Encapsulated herbicide acts by controlled release which takes care of the competing weeds. Moreover, there are adjuvants available for the herbicide. These adjuvants have the nanomaterial employed.

Herbicide paraquat may need a carrier system for action. Silva et al. have prepared the chitosan nanoparticles for this purpose [130]. The characterization of these synthesized nanoparticles was done by the physio-

chemical techniques. Next, the process is followed by the evaluation of pH, zeta potential, and size. For this purpose, various techniques have been employed including the TEM, FTIR, and differential Scanning Calorimetric. Therefore, all these techniques were performed to study the release action of 1, 1'-Dimethyl-4, 4'-bipyridinium (Paraquat), an herbicide containing the chitosan NPs. The results depicted that the paraquat and herbicide release action is altered via the alginate or chitosan nanoparticles.

5.1.1. Detoxification of Herbicides Residues

Crops can sense the damage by the excessive use of herbicides. Whenever herbicides are used in large amounts, the residues can be left behind in the soil. Therefore, using the herbicide over the years will eventually develop the herbicide resistance in the weed growing in that soil and then shift in the weed flora. Broadleaf and grassy weeds have a half-life of nearly 125 days and are also mobile in some soils. These kinds of weeds can be controlled via an herbicide named as Atrazine. This s-triazine-ring herbicide is used globally for this purpose and is now at threat due to residual problems. TNAU, India has raised the hope recently from their study that remediation of residuals of Atrazine is possible within a short time. Silver modified NPs of CMC were applied to remediate the Atrazine residuals from soil and results showed the 88% success rate of degradation of herbicide [131].

5.2. Nanomaterial in Seed Germination

New scientific innovations utilize many approaches and contributed much to the field of Nano sciences recently. This situation has been a one step further towards the nanotech applications in agriculture. Nano science helped in enhancing the growth of crops, the process of seed germination, and adapting to different environments. Population dynamics and well-being of all the species depends significantly on the seed

germination process. Therefore, the germination of seeds is not just a sensitive but important process in the plant's lifecycle. Seed germination, in turn, depends upon multiple factors and attributes i.e. moisture level in soil, nutrients, and soil's compatibility with species [132]. Many studies have been made in this regard and it has been shown that nanomaterial's have contributed much to increasing the plant's growth and overall production of crops. It has been depicted that the utilization of Carbon nanotubes (multi-walled) has shown positive effects on the seed development process of soybean, tomato, corn, barley wheat, and more [133-136]. Similarly, nano silicon dioxide (SiO₂), Titanium Dioxide (TiO₂), and Zeolite have already influenced the seed germination process in a positive manner for various kinds of crops [132, 137]. Another research conducted in this regard depicted that the Iron or Silicon Dioxide nanoparticles play an important role in improving the overall seed germination of particular types of crops mainly Barley and Maize [138]. There has been enough evidences now concerning the advantageous influences of nanomaterial's on seed germination but the actual process behind this is unclear yet. Some studies have reported that after application of nanomaterial, the NPs have the capacity to pass through the seed coat. After passing, they enhance the ability of absorption of water by the seedling. This way, the seedling is better able to grow and germinate under favorable conditions.

Quality enhancement and increase in the crop's yield is also described by employing multiple kinds of nanomaterials. Such nanomaterials include Zinc oxide, Titanium dioxide, carbon nanotubes, Iron Oxide, and ZnFeCu-Oxide [139-141]. Similarly, studies have stated the benefits of the crop growth of OH-functionalized fullerenes via the utilization of carbon nanotubes. Gao *et al.*, (2011) studied the growth of hypocotyl in fullerenes in Arabidopsis via the cell division [142]. Therefore, Fullerol has been found responsible for the enhancement in fruit's growth, size, and the overall yield as well. The

increase found out to be 128% and also it cause an increase in the production of bioactive compounds. These bioactive compounds include the Amarine, ψ,ψ -Carotene, charantin, and Chicory Extract [143]. Yousefzadeh and Sabaghnia described that the nano-iron fertilizer enhanced the essential oil contents of plants [144]. In the same way, the nano-zinc and boron fertilizers are employed for improving the fruit yield and quality. It includes the process of decreasing the total soluble solids by 4.4 - 7.6%, an increase in the titratable acidity by 9.5 - 29.1%, and 0.28-0.62 pH increase in the pomegranate [145]. These evidences are enough to prove the role of nanomaterials in increasing the crop's production and quality. However, the mechanism by which the nanomaterials enhance the growth and quality of plants is still unknown. Some evidences have been found that the nanomaterials increase the intake of nutrients and water and nutrients to improve the root system via increases enzyme activity [139, 140].

Moreover, the studies have also revealed the phenomenon of control or slow release of nanofertilizers in water or soil which helps in availability of nutrients for all the time during cultivation of crops. This availability of nutrients helps to improve the seed sprouting, development, blossoming/flowering, and more [146]. Like, a urea fertilizer (nano-coated in this case) named as hydroxyapatite release the nitrogen contents needed for plant growth at a very slow rate. It releases these contents continuously for 60 days. On the other hand, the traditional fertilizer will end up in 30 days and that too with an unbalanced release. It'll adversely affect the plant's growth and quality of production [147]. In a study, Zheng *et al.*, (2005) researched about the photosynthesis in spinach [148]. They found out that when TiO₂ nanofertilizer is applied, the photosynthesis rate increases by 3.13% but decreased beyond the 4%. Similarly, Disfani *et al.*, (2011) made a research on the size of barley and maize

Table 3. Various nanofertilizers are used in agriculture and their impact on crops

Sr. No	Plant	Nano-fertilizer	Amount of nano-fertilizer (PPM)	Highlights of the study	Ref.
1	<i>Pennisetum glaucum</i>	Au	50	Seedling growth and seed germination	[165]
2	<i>Arachis hypogaea</i>	Ca	-	Plant growth and nutrient contents	[166]
3	<i>Cucumis sativus</i>	CeO ₂	400	Globuline content and food quality	[167]
4	<i>Phoenix dactylifera</i>	CNTs	0.05-0.1	Leaf number and shoot length	[168]
5	<i>Lactuca sativa</i>	Cu	130-600	Shoot length, germination of seeds and effect on soil microbe community	[169]
6	<i>Zea mays</i>	CuO	10	Plant growth and roots	[170]
7	<i>Glycine max</i>	FeO	30-60	Effects of NPs on chlorophyll	[171]
8	<i>Pisum sativum</i>	FeO	250-500	Increased chlorophyll	[172]
9	<i>Vigna unguiculata</i>	Mg	2.5	Increased chlorophyll	[172]
10	<i>Vigna radiata</i>	Mn	0.05-1	Increased chlorophyll	[173]
11	<i>Oryza sativa</i>	Mn	-	Zn uptake improved	[174]
12	<i>Cicer arietinum</i>	Mo	8	Increased plant mas	[175]
13	<i>Glycine max</i>	P	100	Growth rate increased	[176]
14	<i>Spinacia oleracea</i>	TiO ₂	0.25-4	N ₂ fixation improved	[177]
15	<i>Lolium</i>	Zn	1-2000	Root elongation	[178]
16	<i>Vigna radiata</i>	ZnO	1-2000	Growth rate increased	[179]

seedlings and depicted that the application of nanomaterial i.e. nano Fe/SiO₂ caused an increase in length by approx. 8.3% and 21% respectively [138]. But the shoot length has a negative impact on reaching the concentration level above 0.025 g/kg. This means that the growth of crops depend on the nanomaterials. El Feky *et al.* (2013) suggested that the crop's development and quality also depends upon the application of nanomaterials [149]. The foliar applications of nano Fe₃O₄ can increase the total production of chlorophyll, carbohydrate and essential oils content, height, shoot and branches length, and many other factors in *Ocimum basilicum* plants.


5.3. Nano-fertilizers

These are regarded as the nanomaterials which are capable enough to provide nutrients and certain elements to the plants which are needed for their growth and production [150]. Nano fertilizers are categorized as subject to the type of nutrients plants need (table 3).

5.3.1. Macronutrient Nanofertilizer

As mentioned in the name, this fertilizer is for the soil

where nutrients are obligatory in the large amount, especially for the traditional framing. Macronutrients such as Nitrogen, Phosphorus, Sulphur, Magnesium, Potassium, and Calcium are needed for proper growth. Demands for the production of food are increasing continuously which tends to increase the need for Nano fertilizer to 263 MT by 2050 [151]. Nanomaterial has a high volume-to-surface ratio. This brings the utmost efficiency to the applications of macronutrient fertilizer rather than the traditional ones. Therefore, many researchers are working continuously to improve the macronutrients fertilizer to use it at the field scale. In this regard, Liu *et al.* (2014) and Ditta *et al.* (2015) have studied the applications of nanoparticle-based fertilizer [150-152]. Controlled release of Nitrogen has been achieved by the zeolite chips (Urea coated) and urea-modified hydroxyapatite nanoparticles [147, 153]. Similarly, Liu and Lal (2014) have researched on the Calcium and Phosphorus hydroxyapatite nanoparticles which showed an increase of approx. [154]. 20.5% and 34% in the Glycine max seed yield. Liu *et al.* (2005) have noticed a 15% increase in the biomass of *Arachis hypogae* by the application of Ca NP as compared to the



conventional Calcium macronutrient [155]. Moreover, Delfani *et al.* (2014) studied the seed weight of *Vigna unguiculata* [156]. They found the enhancement by 7% in the seed weigh after the application of synthesized Mg NP. The effects of nanofertilizers on plant and soil are illustrated in figure 4.

5.3.2. Micronutrient Nanofertilizer

Though micronutrients are required in smaller quantities but it is necessary for the metabolic process. The bioavailability to the plants is significantly improved in the case of micronutrients and hence enhances the growth and quality of crops. Delfani *et al.* (2004) have made another research on the chlorophyll contents of black-eyed pea after the application of Fe NP which is improved by 10% [156]. Similarly, Ghafariyan *et al.* (2013) have found out 30-60 ppm concentration increase in the chlorophyll content in *G. max* [157]. Using bulk Manganese Sulfate will not provide sufficient increase in growth and quality. Therefore, spraying the Mn NP will enhance the biomass by 37-38%, root length by 52-53%, and shoot length by 38-39%.

Zinc element is responsible to carry out the regulatory mechanism for all the enzyme activities in plants. Zinc Oxide NPs are responsible to enhance or upsurge the

contents of biomass, shoot length, root length, and overall growth by improving the protein content. These improvements can be seen in the *Vigna Radiate*, *Cucumis sativas*, *Raphanus sativus*, *Brassica napus*, and *Cluster bean* [158-161]. Molybdenum NPs when used in combination with the nitrogen fixation bacteria tend to improve the overall seed growth in chickpea [162].

5.3.3. Nano-particulate Fertilizer

Nanoparticles including the Titanium Dioxide, Silicon Dioxide, and carbon nanotubes are significantly responsible to increase the plant's growth and quality of crops. A mixture of Titanium Dioxide, Silicon Dioxide NPs has been seen to improve the seed growth and germination process along with an enhancement in nitrogen fixation in *G. max* [137]. Only the Titanium Dioxide NPs have the ability to improve the chlorophyll, protein, and nitrogen content of the *Spinacia oleracea* [163]. Carbon Nanotubes have been widely used as the fertilizer for diverse species of plants and vegetables. Carbon nanotubes follow the same principle as the nanoparticles and penetrate the seed coat to enhance the water uptake resulting in better growth [164].

5.4. Nano-pesticide

Table 4. Impact on nanopesticides on plants

Nanoparticles	Pathogen	Plant disease	Effect	Ref.
Ag	<i>Xanthomonas campestris pv.campestris</i>	Bacterial blight	Improved bacterial reduction	[183]
Ag core-DHPAC shell	<i>Phytophthora nicotianae</i>	Fungal disease	Growth inhibition	[184]
FeO	<i>F. oxysporum</i>	Fungal disease	Growth inhibition	[185]
Chitosan	<i>Colletotrichum capsici</i>	Diseases in chilli	Reduce mycelia growth rate	[186]
	<i>Macrophomina phaseolina</i>	Fungal disease	Stopped spore germination	[187]
Cu	<i>Fusarium sp</i>	Fungal disease	Antifungal	[188]
	<i>Phytophthora infestans</i>	Disease in tomato	Antifungal	[189]
	<i>Xanthomonas axonopodis pv. punicae</i>	Bacterial blight	Improved bacterial growth inhibition	[190]
Silver-GO composite	<i>Xanthomonas performance</i>	Bacterial Spots	Improved bacterial growth inhibition	[191]

The pesticide industry has an ongoing demand for Nano formulation. In this process, the Nano formulation of traditional pesticide with polymers or metal NPs has advantageous factors to consider. In this regard, the Nano encapsulation of pesticides makes sure the slow release of the ingredients over a prolonged time. This way, you can also reduce the run-off of pesticides [180, 181]. Nano carriers have a similar advantage of site-specific delivery. Another method named as Nano emulsion is getting thoughts of professionals [182]. In this method, the Nano emulsion process can enhance the overall solubility and absorbing capacity of pesticides in soil. The impact of nano pesticides on plants is explained in table 4.

Silver NPs are one of the Nano pesticides which is active against the number of pests in a diverse range of plants including *Botrytis cinerea*, *Colletotrichum*, *Phoma*, and more. Similarly, a combination of Silica and Silver NPs has been proven utmost effective against the powdery mildew [192-195]. Cu nanoparticles are also proven effective against the gram-positive and negative bacteria in low concentration. These NPs were also used against the fungal disease pathogens including *Fusarium sp.*, *Phytophthora infestance* and more [196]. The impact of nanoformulation based materials on pest control is listed in table 5.

Zn NPs is another in the category which was proven effective as nano fertilizer but also as an anti-fungal agent. These NPs were used and found effective against the *Penicillium expansum*, *B. cinerea*, *Apergillus flavus* and more [202-203]. Zinc Oxide NPs have another benefit of being less harmful against the silver NPs. Before making these methods of nanomaterial application to the crops and plants commercial, the control action should be practiced. The Nano-pesticide act must be structured by the centralized organizations in this regard.

5.5. Nanotechnology vs. Traditional carry out

Target framing is getting common these days in nano-agriculture field in which nanoparticles are applied to increase the growth and crop eminence [204, 205]. In terms of seed development or germination and plant growth promotion, the CNTBs (carbon nanotubes) have replaced all other traditional methods [148, 206]. Cu bactericides were used in the past which is now replaced by the nanosized bacteriophages. Their smaller size along with the greater surface to volume ratio makes them more proficient as compared to all other traditional practices. A comparison of nanomaterials and conventional materials is illustrated in figure 5. NPs work in a manner by penetration through the apoplast and then into the epidermal and cortical layers. They accumulate inside as an aggregation [160, 207]. Similarly, Rico *et al.* (2011) studied another penetration pathway i.e. symplastic, and found out as more organized and regulated [208].

6. NANOMATERIAL TOXICITY TO CROPS

6.1. Uptake and movement of nanomaterial

Nanoparticles play a vital role in the study of how a plant responds to different aspects like size, height, and uptake of NPs, and 40-50 nm absorption is observed in the literature [209, 210]. Moreover, coating materials also contribute significantly to the absorption and uptake of nanoparticles. Different species of plants require different quantities of nanoparticles to absorb in a specific time and concentration is provided [210]. A plant can take up nanoparticles via symplastic movement or apoplastic or both [211-213]. Symplastic movement is a result of endocytosis and occurs when nanoparticles cross the outer membrane [214]. NPs are taken up by the plant and reach out to several parts of plants it could be edible like fruits or non-edible like stem, leaf, and roots [215-216].

Table 5. Impact of nanoformulation based materials on pest control

Cam	Pesticides	Pathogen	Plant disease	Effect	Ref.
Porous hollow silica	Validamycin	-	-	36% loading capacity increased	[197]
Cellulose/silica nanocomposites	Tebuconazole	Moulds and rust	Leaf decay	Enhanced release rate	[198]
CaCO ₃	Validamycin	<i>Rhizoctonia solani</i>	-	Controlled release	[199]
Lignin	Diuron	-	-	Controlled release	[200]
TiO ₂	With Ag and Zn	Xanthomonas perforans	Disease in tomato	Improved bacterial reduction	[201]

6.2. Toxicity to crops

Nanoparticles can cause harm to plants in both direct and indirect ways. The high exposure of NPs to plants may adversely affect the growth of roots and leaves and the process of germination as well [217-218]. The most harmful biochemical reactions of nanoparticles include the production of reactive oxygen species in higher amount which affects uptake and movement of water in plants, cause OS (oxidative stress) and problems in photosynthesis and other chemical reactions [219-220].

Many genetic changes were observed in the response to

using various nanoparticles on *N. Tabacum* and *A. cepain*. The toxicity of titanium oxide nanoparticles was compared with copper oxide NPs and cadmium oxide NPs [221-222].

It was concluded that TiO₂ NPs are the least toxic among them and CuO₂ NPs cause high damage to DNA with the formation of 8OH²dG. Hong et al studied that exposure of nCeO₂ over *Cucumis stivus* causes changes in the enzymatic behavior of plants [218]. Damage to chloroplast, destruction of vascular bundle, and variation in uptake of nutrients occur when nan- ceria is applied is provided to cotton plants [223].



Figure 5. A comparison of nanomaterials and conventional materials

7. DETOXIFICATION MECHANISM IN CROPS INDUCED BY NANOMATERIAL

Formation of reactive oxygen species (ROS) is an important harmful mechanism of NPs which badly affects the normal functioning of crops. Nanoparticles are very small in size and have higher activity due to large surface areas which results in higher induction of reactive oxygen species by NPs. Prevention from damages and in the regulation of ROS antioxidants (both enzymatic and non-enzymatic) plays a vital role.

Major antioxidant enzymes are peroxides, SODs, and CAT and GSH and phenolics are the chief non-enzymatic antioxidants. Use of nanoparticles causes changes in the behavior of antioxidants. It has been revealed by studies that exposure of Ag NPs with *R. communis* results in higher production of reactive oxygen species [224]. The toxic effect of Ag NPs in *A. thaliana* is a disturbance in water levels and photosynthesis (by effecting chlorophyll content badly) [225].

Exposure of CuO NPs on *A. thaliana* revealed that toxicity is caused by the release of copper ions [226]. Servin *et al.* (2016) reported that exposure of tin oxide NPs on cucumber cause induction of catalases but no APX activity [216]. The effect of Nd (III) oxide NPs in pumpkin cause higher activities of peroxidase and superoxide dismutases but decreases in the activity of catalases and APX. Rico *et al.* (2011) studied that use of nanoceria in rice has adverse effects on GSH resulting destruction of membranes and photosynthesis [208]. Servin described that upon exposure of tin oxide NPs (250-750mg L⁻¹) cause an increase in catalases activity but no effect on APX activity [216].

8. THREATS OF NANOTECHNOLOGY

The higher growth rate of nanoparticles production and its applications in various areas are well known [227]. The present level of usage and mixing of nanoparticles is not harmful but it cannot be ignored that there is a

chance in increasing the concentration of NPs in the coming years [228-229].

Nanotechnology has its own merits and demerits [230]. NPs can be obtained directly (via natural sources) or indirectly (via anthropogenic production). Nanoparticles are present in soil via rain or supply through agricultural activities. The concentration of NPs is high in the soil as compared to water and air, due to slow movement in soil NPs continue to stay there for a longer period of time [231]. Nano-fertilizers are major source of nanoparticles contamination because plants uptake NPs present in soil and NPs move through the plant and reach to various parts of plants and ultimately to human when human consumes the product of that plant. The adverse effects of NPs include a higher rate of reactive oxygen species, chromosomal aberration, genetic defects, and cause harm to different organs in humans. There are many sites of entry for nanoparticles into the human body. They can enter via breathing, eating, and even by injecting during the medical processes. The major issue is the activities and responsibilities of NPs inside the human body like how nanoparticles behave with tissues and different organs [230]. The cytotoxicity increases when high concentrations of nanoparticles are used. During the past few decades, nanoparticles are being produced on a very large scale and they end up causing toxicity in the environment. Researchers revealed that Ag NPs are used in the making of socks because they help to lessen smell but they affect adversely when released in the wash [232]. Ag NPs are bacteriostatic they may destroy other bacteria which are helpful for the degradation of organic material in waste treatment farms. By knowing the threats of NPs, authorities such as EPA (environmental protection agency) and FDA (food & drug administration) have started taking preventing measures to reduce the risks produced by NPs [230].

9. CONCLUSION

As the need for food grows rapidly, it is important to enhance the productivity of crops. Regarding to improved crop production, it is important to find an advanced solution that can accelerate productivity and not pollute the environment. The integration of nanotechnology in agriculture has provided the final solution needed for the development of the agricultural sector. Nanoparticles modify conventional agricultural particles as they target, control the release of chemicals that are not harmful to soil microorganisms, and unmarked organisms, including crop plants, and ultimately they are not natural. As nano fertilizers release nutrients slowly and consistently, they also reduce the high cost of continuous application of fertilizers. Furthermore, nano fertilizers are highly capable of controlling the environmental pressure of the soil and the active ingredients as required. Although these unique properties of nano-based agricultural particles have made them a viable candidate, nanotechnology is still in its infancy in agriculture. A detailed study of the ecological pathways of these advanced organisms is not yet known and is being explored. When their adverse effects on ecosystems are fully understood and their long-term effects are well explored, the full potential of nanoparticles can be utilized.

10. ACKNOWLEDGEMENT

NA

11. CONFLICT OF INTEREST

The authors have declared that there is no conflict of interest.

12. SOURCE/S OF FUNDING

NA

13. REFERENCES

1. Thakkar, K. N., Mhatre, S. S., & Parikh, R. Y. (2010). Biological synthesis of metallic nanoparticles. *Nanomedicine: nanotechnology, biology and medicine*, **6(2)**: 257-262.
2. Bogunia-Kubik, K., & Sugisaka, M. (2002). From molecular biology to nanotechnology and nanomedicine. *Biosystems*, **65(2-3)**: 123-138.
3. Daniel, M. C., & Astruc, D. (2004). Gold nanoparticles: assembly, supramolecular chemistry, quantum-size-related properties, and applications toward biology, catalysis, and nanotechnology. *Chemical reviews*, **104(1)**: 293-346.
4. Zharov, V. P., Kim, J. W., Curiel, D. T., & Everts, M. (2005). Self-assembling nanoclusters in living systems: application for integrated photothermal nanodiagnostics and nanotherapy. *Nanomedicine: Nanotechnology, Biology and Medicine*, **1(4)**: 326-345.
5. Singh, A., Singh, N. B., Hussain, I., Singh, H., & Singh, S. C. (2015). Plant-nanoparticle interaction: an approach to improve agricultural practices and plant productivity. *Int J Pharm Sci Invent*, **4(8)**: 25-40.
6. Bansal, K., Hooda, V., Verma, N., Kharewal, T., Tehri, N., Dhull, V., & Gahlaut, A. (2022). Stress Alleviation and Crop Improvement Using Silicon Nanoparticles in Agriculture: a Review. *Silicon*, 1-14.
7. Singh, R. P., Handa, R., & Manchanda, G. (2021). Nanoparticles in sustainable agriculture: An emerging opportunity. *Journal of Controlled Release*, **329**, 1234-1248.
8. Li, X., Xu, H., Chen, Z. S., & Chen, G. (2011). Biosynthesis of nanoparticles by microorganisms and their applications. *Journal of Nanomaterials*, 2011.
9. Ahmed, S., Ahmad, M., Swami, B. L., & Ikram, S. (2016). A review on plants extract mediated synthesis of silver nanoparticles for antimicrobial

- applications: a green expertise. *Journal of advanced research*, **7(1)**, 17-28.
10. Rastogi, L., & Arunachalam, J. (2011). Sunlight based irradiation strategy for rapid green synthesis of highly stable silver nanoparticles using aqueous garlic (*Allium sativum*) extract and their antibacterial potential. *Materials Chemistry and Physics*, **129(1-2)**, 558-563.
 11. Azmath, P., Baker, S., Rakshith, D., & Satish, S. (2016). Mycosynthesis of silver nanoparticles bearing antibacterial activity. *Saudi Pharmaceutical Journal*, **24(2)**: 140-146.
 12. Tarafdar, J. C., Sharma, S., & Raliya, R. (2013). Nanotechnology: Interdisciplinary science of applications. *African Journal of Biotechnology*, **12(3)**.
 13. Shalaby, T. A., Bayoumi, Y., Abdalla, N., Taha, H., Alshaal, T., Shehata, S., ... & El-Ramady, H. (2016). Nanoparticles, soils, plants and sustainable agriculture. In *Nanoscience in food and agriculture 1* (pp. 283-312). Springer, Cham.
 14. Buzea, C., Pacheco, I. I., & Robbie, K. (2007). Nanomaterials and nanoparticles: sources and toxicity. *Biointerphases*, **2(4)**: MR17-MR71.
 15. Gnach, A., Lipinski, T., Bednarkiewicz, A., Rybka, J., & Capobianco, J. A. (2015). Upconverting nanoparticles: assessing the toxicity. *Chemical Society Reviews*, **44(6)**: 1561-1584.
 16. Petrovska, B. B. (2012). Historical review of medicinal plants' usage. *Pharmacognosy reviews*, **6(11)**: 1.
 17. Nune, S. K., Chanda, N., Shukla, R., Katti, K., Kulkarni, R. R., Thilakavathy, S., ... & Katti, K. V. (2009). Green nanotechnology from tea: phytochemicals in tea as building blocks for production of biocompatible gold nanoparticles. *Journal of materials chemistry*, **19(19)**: 2912-2920.
 18. Alshatwi, A. A., Athinarayanan, J., & Vaiyapuri Subbarayan, P. (2015). Green synthesis of platinum nanoparticles that induce cell death and G2/M-phase cell cycle arrest in human cervical cancer cells. *Journal of Materials Science: Materials in Medicine*, **26(1)**: 1-9.
 19. Joglekar, S., Kodam, K., Dhaygude, M., & Hudlikar, M. (2011). Novel route for rapid biosynthesis of lead nanoparticles using aqueous extract of *Jatropha curcas* L. latex. *Materials Letters*, **65(19-20)**: 3170-3172.
 20. Iravani, S., & Zolfaghari, B. (2013). Green synthesis of silver nanoparticles using *Pinus eldarica* bark extract. *BioMed research international*, 2013.
 21. Velmurugan, P., Lee, S. M., Iydroose, M., Lee, K. J., & Oh, B. T. (2013). Pine cone-mediated green synthesis of silver nanoparticles and their antibacterial activity against agricultural pathogens. *Applied microbiology and biotechnology*, **97(1)**: 361-368.
 22. Coccia, F., Tonucci, L., Bosco, D., Bressan, M., & d'Alessandro, N. (2012). One-pot synthesis of lignin-stabilised platinum and palladium nanoparticles and their catalytic behaviour in oxidation and reduction reactions. *Green Chemistry*, **14(4)**: 1073-1078.
 23. Song, J. Y., & Kim, B. S. (2009). Rapid biological synthesis of silver nanoparticles using plant leaf extracts. *Bioprocess and biosystems engineering*, **32(1)**: 79-84.
 24. Arundoss, T., & Ar, S. (2013). Mice model of parkinson's disease. *Article info abstract*, **4(10)**: 140-144.
 25. Noruzi, M., Zare, D., & Davoodi, D. (2012). A rapid biosynthesis route for the preparation of gold nanoparticles by aqueous extract of cypress leaves at room temperature. *Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy*, **94**: 84-88.
 26. Sau, T. K., & Murphy, C. J. (2004). Room temperature, high-yield synthesis of multiple

- shapes of gold nanoparticles in aqueous solution. *Journal of the American Chemical Society*, **126(28)**: 8648-8649.
27. Castro, L., Blázquez, M. L., Muñoz, J. A., González, F., & Ballester, A. (2013). Biological synthesis of metallic nanoparticles using algae. *IET nanobiotechnology*, **7(3)**, 109-116.
28. Azizi, S., Ahmad, M. B., Namvar, F., & Mohamad, R. (2014). Green biosynthesis and characterization of zinc oxide nanoparticles using brown marine macroalga *Sargassum muticum* aqueous extract. *Materials Letters*, **116**: 275-277.
29. Jena, J., Pradhan, N., Dash, B. P., Sukla, L. B., & Panda, P. K. (2013). Biosynthesis and characterization of silver nanoparticles using microalga *Chlorococcum humicola* and its antibacterial activity. *Int J Nanomater Biostruct*, **3(1)**, 1-8.
30. Lengke, M. F., Fleet, M. E., & Southam, G. (2006). Synthesis of platinum nanoparticles by reaction of filamentous cyanobacteria with platinum (IV)-chloride complex. *Langmuir*, **22(17)**, 7318-7323.
31. Momeni, S., & Nabipour, I. (2015). A simple green synthesis of palladium nanoparticles with *Sargassum* alga and their electrocatalytic activities towards hydrogen peroxide. *Applied biochemistry and biotechnology*, **176(7)**: 1937-1949.
32. MubarakAli, D., Gopinath, V., Rameshbabu, N., & Thajuddin, N. (2012). Synthesis and characterization of CdS nanoparticles using C-phycoerythrin from the marine cyanobacteria. *Materials Letters*, **74**: 8-11.
33. Govindaraju, K., Kiruthiga, V., Kumar, V. G., & Singaravelu, G. (2009). Extracellular synthesis of silver nanoparticles by a marine alga, *Sargassum wightii* Grevilli and their antibacterial effects. *Journal of Nanoscience and Nanotechnology*, **9(9)**: 5497-5501.
34. Senapati, S., Syed, A., Moez, S., Kumar, A., & Ahmad, A. (2012). Intracellular synthesis of gold nanoparticles using alga *Tetraselmis kochinensis*. *Materials Letters*, **79**: 116-118.
35. Parida, U. K., Bindhani, B. K., & Nayak, P. (2011). Green synthesis and characterization of gold nanoparticles using onion (*Allium cepa*) extract. *World J Nano Sci Eng*, **1(04)**: 93.
36. Von White, G., Kerscher, P., Brown, R. M., Morella, J. D., McAllister, W., Dean, D., & Kitchens, C. L. (2012). Green synthesis of robust, biocompatible silver nanoparticles using garlic extract. *Journal of nanomaterials*: 730746.
37. Daniel, S. C., Ayyappan, S., Philippan, N. J. P., Sivakumar, M., Menaga, G., & Sironmani, T. A. (2011). Green synthesis and transfer of silver nanoparticles in a food chain through *Chironomus* Larva to zebra fish—a new approach for therapeutics. *International Journal of Nanoscience and Nanotechnology*, **2(3)**: 159-169.
38. Shen, D. S., Mathew, J., & Philip, D. (2011). Phytosynthesis of Au, Ag and Au-Ag bimetallic nanoparticles using aqueous extract and dried leaf of *Anacardium occidentale*. *Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy*, **79(1)**: 254-262.
39. Sulochana, S., Krishnamoorthy, P., & Sivaranjani, K. (2012). Synthesis of silver nanoparticles using leaf extract of *Andrographis paniculata*. *J Pharmacol Toxicol*, **7(5)**: 251-258.
40. Kora, A. J., & Arunachalam, J. (2012). Green fabrication of silver nanoparticles by gum tragacanth (*Astragalus gummifer*): a dual functional reductant and stabilizer. *Journal of Nanomaterials*: 869765.
41. Thirumurugan, A., Jiflin, G. J., Rajagomathi, G., Tomy, N. A., Ramachandran, S., & Jaiganesh, R. (2010). Biotechnological synthesis of gold nanoparticles of *Azadirachta indica* leaf extract. *Int J Biol Technol*, **1(1)**: 75-7.

42. Boruah, S. K., Boruah, P. K., Sarma, P., Medhi, C., & Medhi, O. K. (2012). Green synthesis of gold nanoparticles using *Camellia sinensis* and kinetics of the reaction. *Adv Mater Lett*, **3(6)**, 481-6.
43. Jain, D., Daima, H. K., Kachhwaha, S., & Kothari, S. L. (2009). Synthesis of plant-mediated silver nanoparticles using papaya fruit extract and evaluation of their anti-microbial activities. *Digest journal of nanomaterials and biostructures*, **4(3)**: 557-563.
44. Palaniselvam, K., Velangani, A. K., & Govindam, S. (2012). Leaf assisted bioreduction of silver ions using leaves of *Centella asiatica* L and its bioactivity. *Journal of Life Science*, **1(1)**: 46-49.
45. Dwivedi, A. D., & Gopal, K. (2011). Plant-mediated biosynthesis of silver and gold nanoparticles. *Journal of biomedical nanotechnology*, **7(1)**: 163-164.
46. Vanaja, M., & Annadurai, G. (2013). *Coleus aromaticus* leaf extract mediated synthesis of silver nanoparticles and its bactericidal activity. *Applied nanoscience*, **3(3)**: 217-223.
47. Sathishkumar, M., Sneha, K., Kwak, I. S., Mao, J., Tripathy, S. J., & Yun, Y. S. (2009). Phyto-crystallization of palladium through reduction process using *Cinnamom zeylanicum* bark extract. *Journal of Hazardous Materials*, **171(1-3)**: 400-404.
48. Yang, X., Li, Q., Wang, H., Huang, J., Lin, L., Wang, W., ... & Jia, L. (2010). Green synthesis of palladium nanoparticles using broth of *Cinnamomum camphora* leaf. *Journal of Nanoparticle Research*, **12(5)**: 1589-1598.
49. Satyavani, K., Ramanathan, T., & Gurudeeban, S. (2011). Plant mediated synthesis of biomedical silver nanoparticles by using leaf extract of *Citrullus colocynthis*. *Research journal of nanoscience and nanotechnology*, **1(2)**: 95-101.
50. Kesharwani, J., Yoon, K. Y., Hwang, J., & Rai, M. (2009). Phytofabrication of silver nanoparticles by leaf extract of *Datura metel*: hypothetical mechanism involved in synthesis. *Journal of Bionanoscience*, **3(1)**: 39-44.
51. Ahmad, N., Sharma, S., Singh, V. N., Shamsi, S. F., Fatma, A., & Mehta, B. R. (2011). Biosynthesis of silver nanoparticles from *Desmodium triflorum*: a novel approach towards weed utilization. *Biotechnology research international*: 454090.
52. Song, J. Y., Kwon, E. Y., & Kim, B. S. (2010). Biological synthesis of platinum nanoparticles using *Diopyros kaki* leaf extract. *Bioprocess and biosystems engineering*, **33(1)**: 159-164.
53. Ghosh, S., Patil, S., Ahire, M., Kitture, R., Kale, S., Pardesi, K., ... & Chopade, B. A. (2012). Synthesis of silver nanoparticles using *Dioscorea bulbifera* tuber extract and evaluation of its synergistic potential in combination with antimicrobial agents. *International journal of nanomedicine*, **7**: 483.
54. Maheswari, R. U., Prabha, A. L., Nandagopalan, V., & Anburaja, V. (2012). Green synthesis of silver nanoparticles by using rhizome extract of *Dioscorea oppositifolia* L. and their anti microbial activity against human pathogens. *J Pharm Biol Sci*, **1**: 38-42.
55. GnanaJobitha, G., Annadurai, G., & Kannan, C. (2012). Green synthesis of silver nanoparticle using *Elettaria cardamomom* and assesment of its antimicrobial activity. *Int. J. Pharma Sci. Res.(IJPSR)*, **3(3)**: 323-330.
56. Jia, L., Zhang, Q., Li, Q., & Song, H. (2009). The biosynthesis of palladium nanoparticles by antioxidants in *Gardenia jasminoides* Ellis: long lifetime nanocatalysts for p-nitrotoluene hydrogenation. *Nanotechnology*, **20(38)**: 385601.
57. Dinesh, S., Karthikeyan, S., & Arumugam, P. (2012). Biosynthesis of silver nanoparticles from *Glycyrrhiza glabra* root extract. *Arch Appl Sci Res*, **4(1)**: 178-87.
58. Bindhu, M. R., & Umadevi, M. (2013). Synthesis of monodispersed silver nanoparticles using *Hibiscus*

- cannabinus leaf extract and its antimicrobial activity. *Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy*, **101**: 184-190.
59. SABLE, N., GAIKWAD, S., BONDE, S., GADE, A., & RAI, M. (2012). Phytofabrication of silver nanoparticles by using aquatic plant *Hydrilla verticillata*. *Nusantara Bioscience*, **4(2)**.
60. Hudlikar, M., Joglekar, S., Dhaygude, M., & Kodam, K. (2012). Latex-mediated synthesis of ZnS nanoparticles: green synthesis approach. *Journal of Nanoparticle Research*, **14(5)**: 1-6.
61. Fazaludeen, M. F., Manickam, C., Ashankyty, I. M., Ahmed, M. Q., & Beg, Q. Z. (2012). Synthesis and characterizations of gold nanoparticles by *Justicia gendarussa* Burm F leaf extract. *Journal of Microbiology and Biotechnology Research*, **2(1)**: 23-34.
62. Sivakumar, P., Nethradevi, C., & Renganathan, S. (2012). Synthesis of silver nanoparticles using *Lantana camara* fruit extract and its effect on pathogens. *Asian J Pharm Clin Res*, **5(3)**: 97-101.
63. Im, A. R., Han, L., Kim, E. R., Kim, J., Kim, Y. S., & Park, Y. (2012). Enhanced antibacterial activities of *Leonuri herba* extracts containing silver nanoparticles. *Phytotherapy research*, **26(8)**: 1249-1255.
64. Aromal, S. A., Vidhu, V. K., & Philip, D. (2012). Green synthesis of well-dispersed gold nanoparticles using *Macrotyloma uniflorum*. *Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy*, **85(1)**: 99-104.
65. MubarakAli, D., Thajuddin, N., Jeganathan, K., & Gunasekaran, M. (2011). Plant extract mediated synthesis of silver and gold nanoparticles and its antibacterial activity against clinically isolated pathogens. *Colloids and Surfaces B: Biointerfaces*, **85(2)**: 360-365.
66. Vankar, P.S. and D. Bajpai (2010), Preparation of gold nanoparticles from *Mirabilis jalapa* flowers. *Indian J Biochem Biophys*, **47(3)**: 157-60.
67. Jancy, M. E., & Inbathamizh, L. (2012). Green synthesis and characterization of nano silver using leaf extract of *Morinda pubescens*. *Asian J Pharm Clin Res*, **5(Suppl 1)**: 159-162.
68. Ramteke, C., Chakrabarti, T., Sarangi, B. K., & Pandey, R. A. (2013). Synthesis of silver nanoparticles from the aqueous extract of leaves of *Ocimum sanctum* for enhanced antibacterial activity. *Journal of chemistry*.
69. Kumar, D. A. (2012). Rapid and green synthesis of silver nanoparticles using the leaf extracts of *Parthenium hysterophorus*: a novel biological approach. *Int Res J Pharm*, **3(2)**: 169-172.
70. Sundaravadivelan, C., & Nalini, M. (2012). Biolarvicidal effect of phyto-synthesized silver nanoparticles using *Pedilanthus tithymaloides* (L.) Poit stem extract against the dengue vector *Aedes aegypti* L.(Diptera; Culicidae). *Asian Pac. J. Trop. Biomed*, **17**: 1-8.
71. Betle Broth, P. (2012). Phytofabrication and characterization of silver nanoparticles from *Piper betle* broth. *Research Journal of Nanoscience and nanotechnology*, **2(1)**: 17-23.
72. Garg, S. (2012). Rapid biogenic synthesis of silver nanoparticles using black pepper (*Piper nigrum*) corn extract. *Int J Innov Biol Chem Sci*, **3**: 5-10.
73. Patil, C. D., Patil, S. V., Borase, H. P., Salunke, B. K., & Salunkhe, R. B. (2012). Larvicidal activity of silver nanoparticles synthesized using *Plumeria rubra* plant latex against *Aedes aegypti* and *Anopheles stephensi*. *Parasitology Research*, **110(5)**: 1815-1822.
74. Nabikhan, A., Kandasamy, K., Raj, A., & Alikunhi, N. M. (2010). Synthesis of antimicrobial silver nanoparticles by callus and leaf extracts from saltmarsh plant, *Sesuvium portulacastrum* L.

- Colloids and surfaces B: Biointerfaces*, **79(2)**: 488-493.
75. Amin, M., Anwar, F., Janjua, M. R. S. A., Iqbal, M. A., & Rashid, U. (2012). Green synthesis of silver nanoparticles through reduction with *Solanum xanthocarpum* L. berry extract: characterization, antimicrobial and urease inhibitory activities against *Helicobacter pylori*. *International Journal of Molecular Sciences*, **13(8)**: 9923-9941.
76. Njagi, E. C., Huang, H., Stafford, L., Genuino, H., Galindo, H. M., Collins, J. B., ... & Suib, S. L. (2011). Biosynthesis of iron and silver nanoparticles at room temperature using aqueous sorghum bran extracts. *Langmuir*, **27(1)**: 264-271.
77. Petla, R. K., Vivekanandhan, S., Misra, M., Mohanty, A. K., & Satyanarayana, N. (2011). Soybean (*Glycine max*) leaf extract based green synthesis of palladium nanoparticles.
78. Mondal, S., Roy, N., Laskar, R. A., Sk, I., Basu, S., Mandal, D., & Begum, N. A. (2011). Biogenic synthesis of Ag, Au and bimetallic Au/Ag alloy nanoparticles using aqueous extract of mahogany (*Swietenia mahogani* JACQ.) leaves. *Colloids and surfaces B: biointerfaces*, **82(2)**: 497-504.
79. Raghunandan, D., Bedre, M. D., Basavaraja, S., Sawle, B., Manjunath, S. Y., & Venkataraman, A. (2010). Rapid biosynthesis of irregular shaped gold nanoparticles from macerated aqueous extracellular dried clove buds (*Syzygium aromaticum*) solution. *Colloids and Surfaces B: Biointerfaces*, **79(1)**: 235-240.
80. Ankamwar, B. (2010). Biosynthesis of gold nanoparticles (green-gold) using leaf extract of *Terminalia catappa*. *E-Journal of Chemistry*, **7(4)**: 1334-1339.
81. Geethalakshmi, R., & Sarada, D. V. L. (2010). Synthesis of plant-mediated silver nanoparticles using *Trianthema decandra* extract and evaluation of their anti microbial activities. *International Journal of Engineering Science and Technology*, **2(5)**: 970-975.
82. Gopalakrishnan, K., Ramesh, C., Ragunathan, V., & Thamilselvan, M. (2012). Antibacterial activity of Cu₂O nanoparticles on *E. coli* synthesized from *Tridax procumbens* leaf extract and surface coating with polyaniline. *Digest Journal of Nanomaterials and Biostructures*, **7(2)**: 833-839.
83. Pavani, K. V., Swati, T., Snehika, V., Sravya, K., & Sirisha, M. (2012). Phytofabrication of lead nanoparticles using Grape skin extract. *International Journal of Engineering Science and Technology*, **4(7)**.
84. Singh, C., Sharma, V., Naik, P. K., Khandelwal, V., & Singh, H. (2011). A green biogenic approach for synthesis of gold and silver nanoparticles using *Zingiber officinale*. *Digest Journal of Nanomaterials and Biostructures*, **6(2)**: 535-542.
85. Feng, X. X., Zhang, L. L., Chen, J. Y., Guo, Y. H., Zhang, H. P., & Jia, C. I. (2007). Preparation and characterization of novel nanocomposite films formed from silk fibroin and nano-TiO₂. *International journal of biological macromolecules*, **40(2)**: 105-111.
86. Wang, G., YAO, J., ZHOU, X., & SHENG, N. (2008). Preparation of nano silk fibroin/hydroxyapatite biological composite by "one-step" method. *Acta Materiae Compositae Sinica*, **6**: 027.
87. Agrawal, P., & Bhushan, S. (2013). Preparation of sericin nano particles from waste of silk industry. *International Journal of Science Research*, **1(3)**: 116-120.
88. Sahab, A. F., Waly, A. I., Sabbour, M. M., & Nawar, L. S. (2015). Synthesis, antifungal and insecticidal potential of Chitosan (CS)-g-poly (acrylic acid)(PAA) nanoparticles against some seed borne fungi and insects of soybean. *Int J Chem Tech Res*, **8(2)**: 589-598.

89. Sheshmani, S., Ashori, A., & Hasanzadeh, S. (2014). Removal of Acid Orange 7 from aqueous solution using magnetic graphene/chitosan: A promising nano-adsorbent. *International journal of biological macromolecules*, **68**: 218-224.
90. Bhattacharyya, R., & Ray, S. K. (2014). Micro-and nano-sized bentonite filled composite superabsorbents of chitosan and acrylic copolymer for removal of synthetic dyes from water. *Applied clay science*, **101**: 510-520.
91. Mandal, D., Bolander, M. E., Mukhopadhyay, D., Sarkar, G., & Mukherjee, P. (2006). The use of microorganisms for the formation of metal nanoparticles and their application. *Applied microbiology and biotechnology*, **69**(5): 485-492.
92. Thakkar, K. N., Mhatre, S. S., & Parikh, R. Y. (2010). Biological synthesis of metallic nanoparticles. *Nanomedicine: nanotechnology, biology and medicine*, **6**(2): 257-262.
93. Narayanan, K. B., & Sakthivel, N. (2010). Biological synthesis of metal nanoparticles by microbes. *Advances in colloid and interface science*, **156**(1-2): 1-13.
94. Mohanpuria, P., Rana, N. K., & Yadav, S. K. (2008). Biosynthesis of nanoparticles: technological concepts and future applications. *Journal of nanoparticle research*, **10**(3): 507-517.
95. Hulkoti, N. I., & Taranath, T. C. (2014). Biosynthesis of nanoparticles using microbes—a review. *Colloids and Surfaces B: Biointerfaces*, **121**: 474-483.
96. Senapati, S., Ahmad, A., Khan, M. I., Sastry, M., & Kumar, R. (2005). Extracellular biosynthesis of bimetallic Au–Ag alloy nanoparticles. *Small*, **1**(5): 517-520.
97. Vigneshwaran, N., Ashtaputre, N. M., Varadarajan, P. V., Nachane, R. P., Paralikar, K. M., & Balasubramanya, R. H. (2007). Biological synthesis of silver nanoparticles using the fungus *Aspergillus flavus*. *Materials letters*, **61**(6): 1413-1418.
98. Prasad, K., Jha, A. K., & Kulkarni, A. R. (2007). Lactobacillus assisted synthesis of titanium nanoparticles. *Nanoscale Research Letters*, **2**(5): 248-250.
99. Lengke, M. F., Fleet, M. E., & Southam, G. (2006). Synthesis of platinum nanoparticles by reaction of filamentous cyanobacteria with platinum (IV)–chloride complex. *Langmuir*, **22**(17): 7318-7323.
100. Zhang, H., Li, Q., Lu, Y., Sun, D., Lin, X., Deng, X., ... & Zheng, S. (2005). Biosorption and bioreduction of diamine silver complex by *Corynebacterium*. *Journal of Chemical Technology & Biotechnology: International Research in Process, Environmental & Clean Technology*, **80**(3): 285-290.
101. Yong, P., Rowson, N. A., Farr, J. P. G., Harris, I. R., & Macaskie, L. E. (2002). Bioreduction and biocrystallization of palladium by *Desulfovibrio desulfuricans* NCIMB 8307. *Biotechnology and bioengineering*, **80**(4): 369-379.
102. Nair, B., & Pradeep, T. (2002). Coalescence of nanoclusters and formation of submicron crystallites assisted by *Lactobacillus* strains. *Crystal growth & design*, **2**(4): 293-298.
103. Joerger, R., Klaus, T., & Granqvist, C. G. (2000). Biologically produced silver–carbon composite materials for optically functional thin-film coatings. *Advanced Materials*, **12**(6): 407-409.
104. Smith, P. R., Holmes, J. D., Richardson, D. J., Russell, D. A., & Sodeau, J. R. (1998). Photophysical and photochemical characterisation of bacterial semiconductor cadmium sulfide particles. *Journal of the Chemical Society, Faraday Transactions*, **94**(9): 1235-1241.
105. Mann, S., Frankel, R. B., & Blakemore, R. P. (1984). Structure, morphology and crystal growth of bacterial magnetite. *Nature*, **310**(5976): 405-407.

106. Beveridge, T. J., & Murray, R. G. (1980). Sites of metal deposition in the cell wall of *Bacillus subtilis*. *Journal of bacteriology*, **141**(2): 876-887.
107. Sanghi, R., & Verma, P. (2009). Biomimetic synthesis and characterisation of protein capped silver nanoparticles. *Bioresource technology*, **100**(1): 501-504.
108. Vigneshwaran, N., Ashtaputre, N. M., Varadarajan, P. V., Nachane, R. P., Paralikar, K. M., & Balasubramanya, R. H. (2007). Biological synthesis of silver nanoparticles using the fungus *Aspergillus flavus*. *Materials letters*, **61**(6): 1413-1418.
109. Thakkar, K. N., Mhatre, S. S., & Parikh, R. Y. (2010). Biological synthesis of metallic nanoparticles. *Nanomedicine: nanotechnology, biology and medicine*, **6**(2): 257-262.
110. Bansal, V., Poddar, P., Ahmad, A., & Sastry, M. (2006). Room-temperature biosynthesis of ferroelectric barium titanate nanoparticles. *Journal of the American Chemical Society*, **128**(36): 11958-11963..
111. Riddin, T. L., Gericke, M., & Whiteley, C. G. (2006). Analysis of the inter and extracellular formation of platinum nanoparticles by *Fusarium oxysporum* f. sp. *lycopersici* using response surface methodology. *Nanotechnology*, **17**(14): 3482.
112. Bansal, V., Rautaray, D., Bharde, A., Ahire, K., Sanyal, A., Ahmad, A., & Sastry, M. (2005). Fungus-mediated biosynthesis of silica and titania particles. *Journal of Materials Chemistry*, **15**(26): 2583-2589.
113. Senapati, S., Ahmad, A., Khan, M. I., Sastry, M., & Kumar, R. (2005). Extracellular biosynthesis of bimetallic Au-Ag alloy nanoparticles. *Small*, **1**(5): 517-520.
114. Mahmoud, A. W. M., & Taha, S. S. (2018). Main sulphur content in essential oil of *Eruca Sativa* as affected by nano iron and nano zinc mixed with organic manure. *Agriculture*, **64**(2): 65.
115. Velten, S., Leventon, J., Jager, N., & Newig, J. (2015). What is sustainable agriculture? A systematic review. *Sustainability*, **7**(6): 7833-7865.
116. Singh, R. P., Manish, S., Kuldeep, B., Sengar, R. S., & Jaiwal, P. K. (2010). Sustained nutrient supply, reduced nutrient loss and high plant productivity with slow release fertilizers. Stable food production and sustainable agriculture: a challenge ahead in 21st Century, 62-79.
117. Kumar, M., Bauddh, K., Sainger, M., Sainger, P. A., Singh, J. S., & Singh, R. P. (2012). Increase in growth, productivity and nutritional status of rice (*Oryza sativa* L. cv. Basmati) and enrichment in soil fertility applied with an organic matrix entrapped urea. *Journal of Crop Science and Biotechnology*, **15**(2): 137-144.
118. Kumar, M., Bauddh, K., Sainger, M., Sainger, P. A., & Singh, R. P. (2015). Enhancing efficacy of *Azotobacter* and *Bacillus* by entrapping in organic matrix for rice cultivation. *Agroecology and sustainable food Systems*, **39**(8): 907-923.
119. Rai, A., Kumar, S., Bauddh, K., Singh, N., & Singh, R. P. (2017). Improvement in growth and alkaloid content of *Rauwolfia serpentina* on application of organic matrix entrapped biofertilizers (*Azotobacter chroococcum*, *Azospirillum brasilense* and *Pseudomonas putida*). *Journal of Plant Nutrition*, **40**(16): 2237-2247.
120. Campbell, B. M., Thornton, P., Zougmore, R., Van Asten, P., & Lipper, L. (2014). Sustainable intensification: What is its role in climate smart agriculture?. *Current Opinion in Environmental Sustainability*, **8**: 39-43.
121. Kah, M. (2015). Nanopesticides and nanofertilizers: emerging contaminants or opportunities for risk mitigation?. *Frontiers in chemistry*, **3**: 64.
122. Liu, R., & Lal, R. (2015). Potentials of engineered nanoparticles as fertilizers for increasing agronomic

- productions. *Science of the total environment*, **514**: 131-139.
123. Fraceto, L. F., Grillo, R., de Medeiros, G. A., Scognamiglio, V., Rea, G., & Bartolucci, C. (2016). Nanotechnology in agriculture: which innovation potential does it have?. *Frontiers in Environmental Science*, **4**: 20.
124. Viswanathan, S., & Radecki, J. (2008). Nanomaterials in electrochemical biosensors for food analysis-a review. *Polish journal of food and nutrition sciences*, **58(2)**.
125. Sertova, N. M. (2015). Application of nanotechnology in detection of mycotoxins and in agricultural sector. *Journal of Central European Agriculture*.
126. Sekhon, B. S. (2014). Nanotechnology in agri-food production: an overview. *Nanotechnology, science and applications*, **7**: 31.
127. Wilson, M. A., Tran, N. H., Milev, A. S., Kannangara, G. K., Volk, H., & Lu, G. M. (2008). Nanomaterials in soils. *Geoderma*, **146(1-2)**: 291-302.
128. Prasad, R., Bhattacharyya, A., & Nguyen, Q. D. (2017). Nanotechnology in sustainable agriculture: recent developments, challenges, and perspectives. *Frontiers in microbiology*, **8**: 1014.
129. Chinnamuthu, C. R., & Kokiladevi, E. (2007). Weed management through nanoherbicides. *Application of nanotechnology in agriculture*, **10**: 978-971.
130. dos Santos Silva, M., Cocenza, D. S., Grillo, R., de Melo, N. F. S., Tonello, P. S., de Oliveira, L. C., ... & Fraceto, L. F. (2011). Paraquat-loaded alginate/chitosan nanoparticles: preparation, characterization and soil sorption studies. *Journal of hazardous materials*, **190(1-3)**: 366-374.
131. Susha, V., C. Chinnamuthu, and K. Pandian. Remediation of herbicide atrazine through metal nano particle. in International Conference on Magnetic Materials and their Applications in the 21st Century.
132. Manjaiah, K. M., Mukhopadhyay, R., Paul, R., Datta, S. C., Kumararaja, P., & Sarkar, B. (2019). Clay minerals and zeolites for environmentally sustainable agriculture. In *Modified clay and zeolite nanocomposite materials* (pp. 309-329). Elsevier.
133. Lahiani, M. H., Dervishi, E., Chen, J., Nima, Z., Gaume, A., Biris, A. S., & Khodakovskaya, M. V. (2013). Impact of carbon nanotube exposure to seeds of valuable crops. *ACS Applied Materials & Interfaces*, **5(16)**: 7965-7973.
134. Srivastava, A., & Rao, D. P. (2014). Enhancement of seed germination and plant growth of wheat, maize, peanut and garlic using multiwalled carbon nanotubes. *European Chemical Bulletin*, **3(5)**: 502-504.
135. Khodakovskaya, M.V. and A.S. Biris, Method of using carbon nanotubes to affect seed germination and plant growth. 2020, Google Patents.
136. Joshi, A., Kaur, S., Dharamvir, K., Nayyar, H., & Verma, G. (2018). Multi-walled carbon nanotubes applied through seed-priming influence early germination, root hair, growth and yield of bread wheat (*Triticum aestivum* L.). *Journal of the Science of Food and Agriculture*, **98(8)**: 3148-3160.
137. Changmei, L., Chaoying, Z., Junqiang, W., Guorong, W., & Mingxuan, T. (2002). Research of the effect of nanometer materials on germination and growth enhancement of Glycine max and its mechanism. *Soybean Science*, **21(3)**: 168-171.
138. Najafi Disfani, M., Mikhak, A., Kassaei, M. Z., & Maghari, A. (2017). Effects of nano Fe/SiO₂ fertilizers on germination and growth of barley and maize. *Archives of Agronomy and Soil Science*, **63(6)**: 817-826.
139. Dubey, A., & Mailapalli, D. R. (2016). Nanofertilisers, nanopesticides, nanosensors of pest

- and nanotoxicity in agriculture. In *Sustainable agriculture reviews* (pp. 307-330). Springer, Cham.
140. Shojaei, T. R., Salleh, M. A. M., Tabatabaei, M., Mobli, H., Aghbashlo, M., Rashid, S. A., & Tan, T. (2019). Applications of nanotechnology and carbon nanoparticles in agriculture. In *Synthesis, technology and applications of carbon nanomaterials* (pp. 247-277). Elsevier.
141. Shalaby, T. A., Bayoumi, Y., Abdalla, N., Taha, H., Alshaal, T., Shehata, S., ... & El-Ramady, H. (2016). Nanoparticles, soils, plants and sustainable agriculture. In *Nanoscience in food and agriculture 1* (pp. 283-312). Springer, Cham.
142. Gao, J., Wang, Y., Folta, K. M., Krishna, V., Bai, W., Indeglia, P., ... & Moudgil, B. (2011). Polyhydroxy fullerenes (fullerols or fullerenols): beneficial effects on growth and lifespan in diverse biological models. *PLoS One*, **6(5)**: e19976.
143. Kole, C., Kole, P., Randunu, K. M., Choudhary, P., Podila, R., Ke, P. C., ... & Marcus, R. K. (2013). Nanobiotechnology can boost crop production and quality: first evidence from increased plant biomass, fruit yield and phytomedicine content in bitter melon (*Momordica charantia*). *BMC biotechnology*, **13(1)**: 1-10.
144. YOUSEFZADEH, S., & Sabaghnia, N. (2016). Nano-iron fertilizer effects on some plant traits of dragonhead (*Dracocephalum moldavica* L.) under different sowing densities. *Acta agriculturae Slovenica*, **107(2)**: 429-437.
145. Davarpanah, S., Tehranifar, A., Davarynejad, G., Abadía, J., & Khorasani, R. (2016). Effects of foliar applications of zinc and boron nano-fertilizers on pomegranate (*Punica granatum* cv. Ardestani) fruit yield and quality. *Scientia horticulturae*, **210**: 57-64.
146. Lateef, A., Nazir, R., Jamil, N., Alam, S., Shah, R., Khan, M. N., & Saleem, M. (2016). Synthesis and characterization of zeolite based nano-composite: an environment friendly slow release fertilizer. *Microporous and Mesoporous Materials*, **232**: 174-183.
147. Kottegoda, N., Munaweera, I., Madusanka, N., & Karunaratne, V. (2011). A green slow-release fertilizer composition based on urea-modified hydroxyapatite nanoparticles encapsulated wood. *Current science*, 73-78.
148. Zheng, L., Hong, F., Lu, S., & Liu, C. (2005). Effect of nano-TiO₂ on strength of naturally aged seeds and growth of spinach. *Biological trace element research*, **104(1)**: 83-91.
149. Elfeky, S. A., Mohammed, M. A., Khater, M. S., Osman, Y. A., & Elsherbini, E. (2013). Effect of magnetite nano-fertilizer on growth and yield of *Ocimum basilicum* L. *Int. J. Indig. Med. Plants*, **46(3)**: 1286-11293.
150. Liu, R., & Lal, R. (2015). Potentials of engineered nanoparticles as fertilizers for increasing agronomic productions. *Science of the total environment*, **514**: 131-139.
151. Alexandratos, N., & Bruinsma, J. (2012). World agriculture towards 2030/2050: the 2012 revision.
152. Ditta, A., Arshad, M., & Ibrahim, M. (2015). Nanoparticles in sustainable agricultural crop production: applications and perspectives. In *Nanotechnology and plant sciences* (pp. 55-75). Springer, Cham.
153. Millán, G., Agosto, F., Vázquez, M., Botto, L., Lombardi, L., & Juan, L. (2008). Use of clinoptilolite as a carrier for nitrogen fertilizers in soils of the Pampean regions of Argentina. *Cien Inv Agr*, **35(3)**: 293-302.
154. Liu, R., & Lal, R. (2015). Potentials of engineered nanoparticles as fertilizers for increasing agronomic productions. *Science of the total environment*, **514**: 131-139.
155. Xiumei, L., Fudao, Z., Shuqing, Z., Xusheng, H., Rufang, W., Zhaobin, F., & Yujun, W. (2005). Responses of peanut to nano-calcium carbonate.

- Plant Nutrition and Fertilizer Science*, **11(3)**: 385-389.
156. Delfani, M., Baradarn Firouzabadi, M., Farrokhi, N., & Makarian, H. (2014). Some physiological responses of black-eyed pea to iron and magnesium nanofertilizers. *Communications in soil science and plant analysis*, **45(4)**: 530-540.
157. Ghafariyan, M. H., Malakouti, M. J., Dadpour, M. R., Stroeve, P., & Mahmoudi, M. (2013). Effects of magnetite nanoparticles on soybean chlorophyll. *Environmental science & technology*, **47(18)**: 10645-10652.
158. Lin, D., & Xing, B. (2007). Phytotoxicity of nanoparticles: inhibition of seed germination and root growth. *Environmental pollution*, **150(2)**: 243-250.
159. Mahajan, Y.J.N.I. (2011), Nanotechnology-based solutions for oil spills. **2(1)**: 1-19.
160. Zhao, L., Sun, Y., Hernandez-Viezcas, J. A., Servin, A. D., Hong, J., Niu, G., ... & Gardea-Torresdey, J. L. (2013). Influence of CeO₂ and ZnO nanoparticles on cucumber physiological markers and bioaccumulation of Ce and Zn: a life cycle study. *Journal of agricultural and food chemistry*, **61(49)**: 11945-11951.
161. Raliya, R. and J.C.J.A.R. Tarafdar, ZnO nanoparticle biosynthesis and its effect on phosphorous-mobilizing enzyme secretion and gum contents in Clusterbean (*Cyamopsis tetragonoloba* L.). **2(1)**: 48-57.
162. Taran, N. Y., Gonchar, O. M., Lopatko, K. G., Batsmanova, L. M., Patyka, M. V., & Volkogon, M. V. (2014). The effect of colloidal solution of molybdenum nanoparticles on the microbial composition in rhizosphere of *Cicer arietinum* L. *Nanoscale research letters*, **9(1)**: 1-8.
163. Gao, F., Hong, F., Liu, C., Zheng, L., Su, M., Wu, X., ... & Yang, P. (2006). Mechanism of nano-anatase TiO₂ on promoting photosynthetic carbon reaction of spinach. *Biological trace element research*, **111(1)**: 239-253.
164. Srinivasan, C., & Saraswathi, R. (2010). Nano-agriculture-carbon nanotubes enhance tomato seed germination and plant growth. *Current science*, **99(3)**, 274-275.
165. Parveen, A., Mazhari, B. B. Z., & Rao, S. (2016). Impact of bio-nanogold on seed germination and seedling growth in *Pennisetum glaucum*. *Enzyme and Microbial Technology*, **95**: 107-111.
166. Xiumei, L., Fudao, Z., Shuqing, Z., Xusheng, H., Rufang, W., Zhaobin, F., & Yujun, W. (2005). Responses of peanut to nano-calcium carbonate. *Plant Nutrition and Fertilizer Science*, **11(3)**: 385-389.
167. Zhao, L., Peralta-Videa, J. R., Rico, C. M., Hernandez-Viezcas, J. A., Sun, Y., Niu, G., ... & Gardea-Torresdey, J. L. (2014). CeO₂ and ZnO nanoparticles change the nutritional qualities of cucumber (*Cucumis sativus*). *Journal of agricultural and food chemistry*, **62(13)**: 2752-2759.
168. Taha, R. A., Hassan, M. M., Ibrahim, E. A., Abou Baker, N. H., & Shaaban, E. A. (2016). Carbon nanotubes impact on date palm in vitro cultures. *Plant Cell, Tissue and Organ Culture (PCTOC)*, **127(2)**: 525-534.
169. Shah, V., & Belozerovala, I. (2009). Influence of metal nanoparticles on the soil microbial community and germination of lettuce seeds. *Water, air, and soil pollution*, **197(1)**: 143-148.
170. Adhikari, T., Sarkar, D., Mashayekhi, H., & Xing, B. (2016). Growth and enzymatic activity of maize (*Zea mays* L.) plant: solution culture test for copper dioxide nano particles. *Journal of Plant Nutrition*, **39(1)**: 99-115.
171. Ghafariyan, M. H., Malakouti, M. J., Dadpour, M. R., Stroeve, P., & Mahmoudi, M. (2013). Effects of magnetite nanoparticles on soybean chlorophyll.

- Environmental science & technology*, **47(18)**: 10645-10652.
172. Delfani, M., Baradarn Firouzabadi, M., Farrokhi, N., & Makarian, H. (2014). Some physiological responses of black-eyed pea to iron and magnesium nanofertilizers. *Communications in soil science and plant analysis*, **45(4)**: 530-540.
173. Pradhan, S., Patra, P., Das, S., Chandra, S., Mitra, S., Dey, K. K., ... & Goswami, A. (2013). Photochemical modulation of biosafe manganese nanoparticles on *Vigna radiata*: a detailed molecular, biochemical, and biophysical study. *Environmental Science & Technology*, **47(22)**: 13122-13131.
174. Yuvaraj, M., & Subramanian, K. S. (2015). Controlled-release fertilizer of zinc encapsulated by a manganese hollow core shell. *Soil science and plant nutrition*, **61(2)**: 319-326.
175. Taran, N. Y., Gonchar, O. M., Lopatko, K. G., Batsmanova, L. M., Patyka, M. V., & Volkogon, M. V. (2014). The effect of colloidal solution of molybdenum nanoparticles on the microbial composition in rhizosphere of *Cicer arietinum* L. *Nanoscale research letters*, **9(1)**: 1-8.
176. Liu, R., & Lal, R. (2014). Synthetic apatite nanoparticles as a phosphorus fertilizer for soybean (*Glycine max*). *Scientific reports*, **4(1)**: 1-6.
177. Zheng, L., Hong, F., Lu, S., & Liu, C. (2005). Effect of nano-TiO₂ on strength of naturally aged seeds and growth of spinach. *Biological trace element research*, **104(1)**: 83-91.
178. Lin, D., & Xing, B. (2008). Root uptake and phytotoxicity of ZnO nanoparticles. *Environmental science & technology*, **42(15)**: 5580-5585.
179. Mahajan, P., Dhoke, S. K., & Khanna, A. S. (2011). Effect of nano-ZnO particle suspension on growth of mung (*Vigna radiata*) and gram (*Cicer arietinum*) seedlings using plant agar method. *Journal of Nanotechnology*, 2011.
180. Agrawal, S., & Rathore, P. (2014). Nanotechnology pros and cons to agriculture: a review. *Int J Curr Microbiol App Sci*, **3(3)**: 43-55.
181. Pérez-de-Luque, A., & Rubiales, D. (2009). Nanotechnology for parasitic plant control. *Pest Management Science: formerly Pesticide Science*, **65(5)**: 540-545.
182. Nair, R., Varghese, S. H., Nair, B. G., Maekawa, T., Yoshida, Y., & Kumar, D. S. (2010). Nanoparticulate material delivery to plants. *Plant science*, **179(3)**: 154-163.
183. Rajesh, S., Raja, D. P., Rathi, J. M., & Sahayaraj, K. (2012). Biosynthesis of silver nanoparticles using *Ulva fasciata* (Delile) ethyl acetate extract and its activity against *Xanthomonas campestris* pv. *malvacearum*. *Journal of Biopesticides*, **5**: 119.
184. Ho, V. A., Le, P. T., Nguyen, T. P., Nguyen, C. K., Nguyen, V. T., & Tran, N. Q. (2015). Silver core-shell nanoclusters exhibiting strong growth inhibition of plant-pathogenic fungi. *Journal of Nanomaterials*, 2015.
185. Chhipa, H., & Kaushik, N. (2015, November). Development of nano-bio-pesticide using Iron and Eucalyptus plant extract and their application in pest management. In Conference Proceeding of symposium on recent advances in biotechnology for food and fuel, TERI, New Delhi (pp. 19-20).
186. Chookhongkha, N., Sopondilok, T., & Photchanachai, S. (2012). Effect of chitosan and chitosan nanoparticles on fungal growth and chilli seed quality. In I International Conference on Postharvest Pest and Disease Management in Exporting Horticultural Crops-PPDM2012 973 (231-237).
187. Saharan, V., Mehrotra, A., Khatik, R., Rawal, P., Sharma, S. S., & Pal, A. (2013). Synthesis of chitosan based nanoparticles and their in vitro evaluation against phytopathogenic fungi. *International journal of biological macromolecules*, **62**: 677-683.

188. Bramhanwade, K., Shende, S., Bonde, S., Gade, A., & Rai, M. (2016). Fungicidal activity of Cu nanoparticles against Fusarium causing crop diseases. *Environmental chemistry letters*, **14**(2): 229-235.
189. Giannousi, K., Avramidis, I., & Dendrinou-Samara, C. (2013). Synthesis, characterization and evaluation of copper based nanoparticles as agrochemicals against Phytophthora infestans. *RSC advances*, **3**(44): 21743-21752.
190. Mondal, K. K., & Mani, C. (2012). Investigation of the antibacterial properties of nanocopper against Xanthomonas axonopodis pv. punicae, the incitant of pomegranate bacterial blight. *Annals of microbiology*, **62**(2): 889-893.
191. Ocoy, I., Paret, M. L., Ocoy, M. A., Kunwar, S., Chen, T., You, M., & Tan, W. (2013). Nanotechnology in plant disease management: DNA-directed silver nanoparticles on graphene oxide as an antibacterial against Xanthomonas perforans. *Acs Nano*, **7**(10): 8972-8980.
192. Park, K.J.P.m.a.w.f.b.u.s.n., Korea Patent Application: WPI ACC NO: 2006-489267/200650. 2006.
193. Gajbhiye, M., Kesharwani, J., Ingle, A., Gade, A., & Rai, M. (2009). Fungus-mediated synthesis of silver nanoparticles and their activity against pathogenic fungi in combination with fluconazole. *Nanomedicine: Nanotechnology, Biology and Medicine*, **5**(4): 382-386.
194. Sharon, M., Choudhary, A. K., & Kumar, R. (2010). Nanotechnology in agricultural diseases and food safety. *Journal of Phytology*, **2**(4).
195. Gopal, M. A. D. H. U. B. A. N., Gogoi, R. O. B. I. N., Srivastava, C. H. I. T. R. A., Kumar, R. A. J. E. S. H., Singh, P. K., Nair, K. K., ... & Goswami, A. R. U. N. A. V. A. (2011). Nanotechnology and its application in plant protection. *Plant pathology in India: vision, 2030*, 224-232.
196. Cioffi, N., Torsi, L., Ditaranto, N., Tantillo, G., Ghibelli, L., Sabbatini, L., ... & Traversa, E. (2005). Copper nanoparticle/polymer composites with antifungal and bacteriostatic properties. *Chemistry of Materials*, **17**(21): 5255-5262.
197. Liu, X. M., Feng, Z. B., Zhang, F. D., Zhang, S. Q., & He, X. S. (2006). Preparation and testing of cementing and coating nano-subnanocomposites of slow/controlled-release fertilizer. *Agricultural Sciences in China*, **5**(9): 700-706.
198. Mattos, B. D., & Magalhães, W. L. (2016). Biogenic nanosilica blended by nanofibrillated cellulose as support for slow-release of tebuconazole. *Journal of Nanoparticle Research*, **18**(9): 1-10.
199. Qian, K., Shi, T., Tang, T., Zhang, S., Liu, X., & Cao, Y. (2011). Preparation and characterization of nano-sized calcium carbonate as controlled release pesticide carrier for validamycin against Rhizoctonia solani. *Microchimica Acta*, **173**(1): 51-57.
200. Yearla, S. R., & Padmasree, K. (2016). Exploitation of subabul stem lignin as a matrix in controlled release agrochemical nanoformulations: a case study with herbicide diuron. *Environmental Science and Pollution Research*, **23**(18): 18085-18098.
201. Paret, M. L., Vallad, G. E., Averett, D. R., Jones, J. B., & Olson, S. M. (2013). Photocatalysis: effect of light-activated nanoscale formulations of TiO₂ on Xanthomonas perforans and control of bacterial spot of tomato. *Phytopathology*, **103**(3): 228-236.
202. Jayaseelan, C., Rahuman, A. A., Kirthi, A. V., Marimuthu, S., Santhoshkumar, T., Bagavan, A., ... & Rao, K. B. (2012). Novel microbial route to synthesize ZnO nanoparticles using Aeromonas hydrophila and their activity against pathogenic bacteria and fungi. *Spectrochimica Acta Part A*:

- Molecular and Biomolecular Spectroscopy*, **90**: 78-84.
203. He, L., Liu, Y., Mustapha, A., & Lin, M. (2011). Antifungal activity of zinc oxide nanoparticles against *Botrytis cinerea* and *Penicillium expansum*. *Microbiological research*, **166(3)**: 207-215.
204. Batsmanova, L. M., Gonchar, L. M., Taran, N. Y., & Okanenko, A. A. (2013). Using a colloidal solution of metal nanoparticles as micronutrient fertiliser for cereals (Doctoral dissertation, Sumy State University).
205. Scott, N., & Chen, H. (2013). Nanoscale science and engineering for agriculture and food systems. *Industrial Biotechnology*, **9(1)**: 17-18.
206. Khodakovskaya, M. V., Kim, B. S., Kim, J. N., Alimohammadi, M., Dervishi, E., Mustafa, T., & Cernigla, C. E. (2013). Carbon nanotubes as plant growth regulators: effects on tomato growth, reproductive system, and soil microbial community. *Small*, **9(1)**: 115-123.
207. Larue, C., Laurette, J., Herlin-Boime, N., Khodja, H., Fayard, B., Flank, A. M., ... & Carriere, M. (2012). Accumulation, translocation and impact of TiO₂ nanoparticles in wheat (*Triticum aestivum* spp.): influence of diameter and crystal phase. *Science of the total environment*, **431**: 197-208.
208. Rico, C. M., Majumdar, S., Duarte-Gardea, M., Peralta-Videa, J. R., & Gardea-Torresdey, J. L. (2011). Interaction of nanoparticles with edible plants and their possible implications in the food chain. *Journal of agricultural and food chemistry*, **59(8)**: 3485-3498.
209. Corredor, E., Testillano, P. S., Coronado, M. J., González-Melendi, P., Fernández-Pacheco, R., Marquina, C., ... & Risueño, M. C. (2009). Nanoparticle penetration and transport in living pumpkin plants: in situsubcellular identification. *BMC plant biology*, **9(1)**: 1-11.
210. Larue, C., Veronesi, G., Flank, A. M., Surble, S., Herlin-Boime, N., & Carrière, M. (2012). Comparative uptake and impact of TiO₂ nanoparticles in wheat and rapeseed. *Journal of Toxicology and Environmental Health, Part A*, **75(13-15)**: 722-734.
211. Sattelmacher, B. (2001). The apoplast and its significance for plant mineral nutrition. *New Phytologist*, **149(2)**: 167-192.
212. Roberts, A. (2003). Plasmodesmata and the control of symplastic transport. *Plant Cell Environ. Plant, Cell and Environment*, **26**: 103-124.
213. Wang, Z., Xie, X., Zhao, J., Liu, X., Feng, W., White, J. C., & Xing, B. (2012). Xylem-and phloem-based transport of CuO nanoparticles in maize (*Zea mays* L.). *Environmental science & technology*, **46(8)**: 4434-4441.
214. Etxeberria, E., Gonzalez, P., Baroja-Fernandez, E., & Romero, J. P. (2006). Fluid phase endocytic uptake of artificial nano-spheres and fluorescent quantum dots by sycamore cultured cells: evidence for the distribution of solutes to different intracellular compartments. *Plant signaling & behavior*, **1(4)**: 196-200.
215. Koo, Y., Wang, J., Zhang, Q., Zhu, H., Chehab, E. W., Colvin, V. L., ... & Braam, J. (2015). Fluorescence reports intact quantum dot uptake into roots and translocation to leaves of *Arabidopsis thaliana* and subsequent ingestion by insect herbivores. *Environmental science & technology*, **49(1)**: 626-632.
216. Servin, A. D., Morales, M. I., Castillo-Michel, H., Hernandez-Viezcas, J. A., Munoz, B., Zhao, L., ... & Gardea-Torresdey, J. L. (2013). Synchrotron verification of TiO₂ accumulation in cucumber fruit: a possible pathway of TiO₂ nanoparticle transfer from soil into the food chain. *Environmental Science & Technology*, **47(20)**: 11592-11598.

217. Shen, C. X., Zhang, Q. F., Li, J., Bi, F. C., & Yao, N. (2010). Induction of programmed cell death in Arabidopsis and rice by single-wall carbon nanotubes. *American Journal of Botany*, **97(10)**: 1602-1609.
218. Hong, J., Wang, L., Sun, Y., Zhao, L., Niu, G., Tan, W., ... & Gardea-Torresdey, J. L. (2016). Foliar applied nanoscale and microscale CeO₂ and CuO alter cucumber (*Cucumis sativus*) fruit quality. *Science of the Total Environment*, **563**: 904-911.
219. Valavanidis, A., Vlachogianni, T., & Fiotakis, C. (2009). 8-hydroxy-2'-deoxyguanosine (8-OHdG): a critical biomarker of oxidative stress and carcinogenesis. *Journal of environmental science and health Part C*, **27(2)**: 120-139.
220. Wang, X., Yang, X., Chen, S., Li, Q., Wang, W., Hou, C., ... & Wang, S. (2016). Zinc oxide nanoparticles affect biomass accumulation and photosynthesis in Arabidopsis. *Frontiers in plant science*, **6**: 1243.
221. Ghosh, M., Bandyopadhyay, M., & Mukherjee, A. (2010). Genotoxicity of titanium dioxide (TiO₂) nanoparticles at two trophic levels: plant and human lymphocytes. *Chemosphere*, **81(10)**: 1253-1262.
222. Zhu, X., Hondroulis, E., Liu, W., & Li, C. Z. (2013). Biosensing approaches for rapid genotoxicity and cytotoxicity assays upon nanomaterial exposure. *Small*, **9(9-10)**: 1821-1830.
223. Prasad, R., Kumar, M., & Varma, A. (2015). Role of PGPR in soil fertility and plant health. In *Plant-growth-promoting rhizobacteria (PGPR) and medicinal plants* (pp. 247-260). Springer, Cham.
224. Yasur, J., & Rani, P. U. (2013). Environmental effects of nanosilver: impact on castor seed germination, seedling growth, and plant physiology. *Environmental Science and Pollution Research*, **20(12)**: 8636-8648.
225. Qi, M., Liu, Y., & Li, T. (2013). Nano-TiO₂ improve the photosynthesis of tomato leaves under mild heat stress. *Biological trace element research*, **156(1)**: 323-328.
226. Tang, Y., He, R., Zhao, J., Nie, G., Xu, L., & Xing, B. (2016). Oxidative stress-induced toxicity of CuO nanoparticles and related toxicogenomic responses in Arabidopsis thaliana. *Environmental pollution*, **212**: 605-614.
227. Piccinno, F., Gottschalk, F., Seeger, S., & Nowack, B. (2012). Industrial production quantities and uses of ten engineered nanomaterials in Europe and the world. *Journal of nanoparticle research*, **14(9)**: 1-11.
228. Johnson, A. C., & Park, B. (2012). Predicting contamination by the fuel additive cerium oxide engineered nanoparticles within the United Kingdom and the associated risks. *Environmental Toxicology and Chemistry*, **31(11)**: 2582-2587.
229. Nicolodi, M., & Gianello, C. (2014). Understanding soil as an open system and fertility as an emergent property of the soil system. *Sustainable Agriculture Research*, **4**(526-2016-37873).
230. Kumar, A., Gupta, K., Dixit, S., Mishra, K., & Srivastava, S. (2019). A review on positive and negative impacts of nanotechnology in agriculture. *International Journal of Environmental Science and Technology*, **16(4)**: 2175-2184.
231. Gottschalk, F., & Nowack, B. (2011). The release of engineered nanomaterials to the environment. *Journal of Environmental Monitoring*, **13(5)**: 1145-1155.
232. Khan, I., Saeed, K., & Khan, I. (2019). Nanoparticles: Properties, applications and toxicities. *Arabian journal of chemistry*, **12(7)**: 908-931.